





**Cables Cadenas
y Bandas de México**
S.A. de C.V.

Bright Wire Rope - 6 X 37 Class



6 X 36 Warrington
Seale With Fiber Core

Diameter in Inches	FIBER CORE (IPS)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
1/4	0.105	2.74
5/16	0.164	4.26
3/8	0.236	6.1
7/16	0.32	8.27
1/2	0.42	10.7
9/16	0.53	13.5
5/8	0.66	16.7
3/4	0.95	23.8
7/8	1.29	32.2
1	1.68	41.8
1.1/8	2.13	52.6
1.1/4	2.63	64.6
1.3/8	3.18	77.7
1.1/2	3.78	92
1.3/4	5.15	124
2	6.72	160
2.1/4	8.51	200
2.1/2	10.5	244



6 X 36 Warrington
Seale With IWRC


Diameter in Inches	IWRC (EIPS)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
1/4	.116	3.4
5/16	0.18	5.27
3/8	0.26	7.55
7/16	0.35	10.2
1/2	0.46	13.3
9/16	0.59	16.8
5/8	0.72	20.6
3/4	1.04	29.4
7/8	1.42	39.8
1	1.85	51.7
1.1/8	2.34	65
1.1/4	2.89	79.9
1.3/8	3.5	96
1.1/2	4.16	114
1.5/8	4.88	132
1.3/4	5.67	153
2	7.39	198
2.1/4	9.36	247
2.1/2	11.6	302
2.3/4	14	368
3	16.6	428

According to Federal Specification RR-W-410D, preformed, right regular lay, medium lubrication. Read important warnings and information preceding wire rope section. *Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.




**Cables Cadenas
y Bandas de México**
S.A. de C.V.


Bright Wire Rope - 6 X 19 Class




**6 X 25 Filler Wire
With Fiber Core**



**6 X 19 Seale
With Iwrc**



**6 X 25 Filler Wire
With Iwrc**



**6 X 26 Warrington
Seale With Iwrc**

Diameter in Inches	FIBER CORE (IPS)	
	Approx. Weight per foot in Pounds	Breaking Strenght in Tons*
1/4	0.105	2.74
5/16	0.164	4.26
3/8	0.236	6.10
7/16	0.32	8.27
1/2	0.42	10.70
9/16	0.53	13.50
5/8	0.66	16.70
3/4	0.95	23.80
7/8	1.29	32.20
1	1.68	41.80
1.1/8	2.13	52.60
1.1/4	2.63	64.60
1.3/8	3.18	77.70
1.1/2	3.78	92.00
1.3/4	5.15	124.00
2	6.72	160.00
2.1/4	8.51	200.00
2.1/2	10.50	244.00

Diameter in Inches	IWRC (EIPS)	
	Approx. Weight per foot in Pounds	Breaking Strenght in Tons*
1/4	0.116	3.40
5/16	0.18	5.27
3/8	0.26	7.55
7/16	0.35	10.20
1/2	0.46	13.30
9/16	0.59	16.80
5/8	0.72	20.60
3/4	1.04	29.40
7/8	1.42	39.80
1	1.85	51.70
1.1/8	2.34	65.00
1.1/4	2.89	79.90
1.3/8	3.50	96.00
1.1/2	4.16	114.00
1.5/8	4.88	132.00
1.3/4	5.67	153.00
2	7.39	198.00
2.1/4	9.36	247.00
2.3/8	10.40	274.00
2.1/2	11.60	302.00

According to Federal Specification RR-W-410D, preformed, right regular lay, medium lubrication. Read important warnings and information preceding wire rope section. NOTE: Lang lay, left lay, alternate lay, seale available in some sizes. *Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.